nox-crete®

chemical solutions to concrete problems

DECORATIVE

Decorative Cures & Seals and Decorative Sealers Fact Sheet

		Percent Solids	Durability	Carrier	VOC (g/L)	UV Resistance	Substrate Penetration	Touch Dry-Time 70°F (21°C)	Ease of Application	VOLATILE ORGANIC COMPOUND (VOC) REGULATORY COMPLIANCE							
										USEPA	OTC I	OTC II	AZ-MCAQMD	CARB-2000	CARB-2007	CARB-20/SCAQMD	CANADA
Decorative Cures & Seals	Cure & Seal 309	15	Good	Solvent	350	4	5	4	4	■	■						■
	Cure & Seal 1200 E	11	Good	Water	50	5	4	2	5	■	■	■	■	■	■	■	■
	Cure & Seal 1315 A 700	25	Good	Solvent	700	4	3	3	5	■							
	Cure & Seal 1315 A 350	25	Good	Solvent	350	4	3	4	4	■	■						■
	Cure & Seal HG	21	Good	Solvent	100	4	4	4	4	■	■	■	■	■	■	■	■
	Cure & Seal LG	13	Good	Solvent	100	4	5	4	4	■	■	■	■	■	■	■	■
	Tri-Shield 350	16	Best	Solvent	350	5	5	4	4	■	■			■	■	■	■
	Tri-Shield 100	16	Best	Solvent	100	5	5	4	5	■	■	■	■	■	■	■	■
Decorative Sealers	Natraseal 350	15	Best	Solvent	350	5	5	4	4	■	■	■					■
	Sparkl-Seal 700	25	Best	Solvent	700	5	3	3	5	■							
	Sparkl-Seal 350	25	Best	Solvent	350	5	4	4	4	■	■						■
	Sparkl-Seal 100	21	Best	Solvent	100	5	4	4	5	■	■	■	■	■	■	■	■
	Sparkl-Seal E	17	Best	Water	100	5	3	2	5	■	■	■		■	■	■	■

Scale 1 (least or slowest) — **5** (most or fastest)

Blue is VOC Compliant

1444 S. 20th St. Omaha, NE 68108 | 402-341-2080 | www.nox-crete.com