

NOX-CRETE DURO-FLOOR CLASSIC SYSTEM STAIN RESISTANCE TESTING SUMMARY

TESTING SUMMARY: Stain Resistance - ASTM D 1308

Concrete test specimens were diamond ground to lightly remove a thin layer of the cement paste and then polished up to 800 grit. Two coats of DURO-NOX LSC were applied during the polishing process at approximately 700 to 800 sf/gal per coat. After 24 hours, two coats of DURO-POLISH PLUS** were applied using a 2:1 dilution ratio with water at an approximate coverage rate of 1,000 sf/gal per coat. The test specimens were allowed to air cure at room temperature for seven days before testing.

RATING SCALE

| APPEARANCE OF DURO-FLOOR CLASSIC SYSTEM | | APPEARANCE OF CONCRETE | | |
|---|--|--|--|--|
| 1 = Excellent | | A = Excellent (No Concrete Surface Damage) | | |
| 2 = Good | | B = Good (Slight Staining) | | |
| 3 = Fair | | C = Fair (Concrete Surface Etching with Slight Staining Possible) | | |
| 4 = Poor | | D = Poor (Significant Concrete Surface Etching and Staining) | | |
| 5 = Failure - Not Recommended | | F = Failure - Not Recommended (Severe Concrete Etching and Staining) | | |

| | 15 Minutes | 1 Hour | 4 Hours |
|---|------------|--------|---------|
| ACIDS | | | |
| 10% Citric | 1A | 1A | 1A |
| 10% Acetic | 1A | 2B | 3C |
| 10% Hydrochloric | 1A | 5C | 5D |
| ALCOHOL | | | |
| Ethyl Alcohol | 1A | 1A | 1A |
| Ethylene Glycol / Diethylene Glycol Mix | 1A | 1A | 1A |
| SALTS | | | |
| Calcium Chloride | 1A | 1A | 1A |
| Sodium Chloride | 1A | 1A | 1A |
| BASES | | | |
| 30% Ammonium Hydroxide | 1A | 2B | 2B |
| 45% Potassium Hydroxide | 1A | 1A | 1A |
| 50% Sodium Hydroxide | 1A | 1A | 1A |
| SOLVENTS | | | |
| Mineral Spirits | 1A | 1A | 1A |
| Xylene | 1A | 1A | 1A |

| | 15 Minutes | 1 Hour | 4 Hours |
|--------------------------|------------|--------|---------|
| OILS | | | |
| Gasoline | 1A | 1A | 1A |
| Brake Fluid | 1A | 2B | 2B |
| Motor Oil | 1A | 1A | 1A |
| ATF | 1A | 1A | 1A |
| OTHERS | | | |
| Cola | 1A | 1A | 1A |
| Mustard | 1A | 1A | 2C |
| Ketchup | 1A | 1A | 1A |
| Red Wine | 1A | 1A | 1A |
| Balsamic Vinegar | 1A | 1A | 1A |
| Vegetable Oil | 1A | 1A | 1A |
| Bleach | 1A | 2B | 2B |
| Tap Water | 1A | 1A | 1A |
| Liquid Laundry Detergent | 1A | 1A | 1A |
| Lemon Juice | 1A | 1A | 1A |

* Testing was conducted in a laboratory under controlled conditions. Slight differences in results are possible due to differences in concrete mix designs, surface finish and environmental conditions.

** Equivalency testing was conducted using the recommended coverage rate for Duro-Guard and Duro-Polish showing comparable performance in regard to stain blocking capability. Similar performance can be expected for these products.